

Heatshrink : HSTW Clear

Flame retardent, multi purpose, -55°C - 135°C, shrink temp 110°C

Size	As Supplied	After Recovery	
mm	Internal Diameter mm	Internal Diameter MAX mm	Wall Thickness NOM mm
0.8	1.2	0.6	0.41 +/- 0.08
1	1.6	0.8	0.43 +/- 0.08
2	2.4	1.2	0.51 +/- 0.08
3	3.2	1.6	0.51 +/- 0.08
4.5	4.8	2.4	0.51 +/- 0.08
6	6.4	3.2	0.64 +/- 0.08
9	9.5	4.8	0.64 +/- 0.08
12	12.7	6.4	0.64 +/- 0.08
16	15.9	8	0.76 +/- 0.08
18	19.1	9.5	0.76 +/- 0.08
25	25.4	12.7	0.89 +/- 0.12
40	38.1	19.1	1.02 +/- 0.12
50	50.8	25.4	1.14 +/- 0.12
80	76.2	38.1	1.27 +/- 0.12
100	101.6	50.8	1.40 +/- 0.20

Heatshrink: HSTW *all except Clear*

Zero halogen, flame retardent,-45°C - 125°C,shrink temp 120°C

Size	As Supplied	After Recovery	
mm	Internal Diameter mm	Internal Diameter MAX mm	Wall Thickness NOM mm
0.8	1.1 ± 0.2	0.50	0.22
1	1.5 ± 0.2	0.65	0.28
1.5	2.0 ± 0.2	0.85	0.32
2	2.5 ± 0.2	1.00	0.35
2.5	3.0 ± 0.2	1.30	0.38
3	3.5 ± 0.2	1.50	0.40
3.5	4.0 ± 0.2	1.80	0.42
4	4.5 ± 0.2	2.00	0.45
4.5	5.0 ± 0.2	2.30	0.50
5	5.5 ± 0.2	2.5	0.55
6	6.5 ± 0.2	3.0	0.55
7	7.5 ± 0.3	3.5	0.55
8	8.5 ± 0.3	4.0	0.60
9	9.5 ± 0.3	4.5	0.60
10	10.5 ± 0.3	5.0	0.60
11	11.5 ± 0.3	5.5	0.60
12	12.5 ± 0.3	6.0	0.60
13	13.5 ± 0.3	6.5	0.65
14	14.5 ± 0.3	7.0	0.65
15	15.5 ± 0.4	7.5	0.70
16	16.5 ± 0.4	8.0	0.70
17	17.5 ± 0.4	8.5	0.70
18	19.0 ± 0.5	9.0	0.80
20	21.0 ± 0.5	10.0	0.80

Heatshrink: HSTW *all except Clear***Zero halogen, flame retardent,-45°C - 125°C,shrink temp 120°C**

Size	As Supplied	After Recovery	
mm	Internal Diameter mm	Internal Diameter MAX mm	Wall Thickness NOM mm
22	23.0 ± 0.5	11.0	0.80
25	26.0 ± 0.5	12.5	0.90
28	29.0 ± 0.5	14.0	0.90
30	31.5 ± 1.0	15.0	0.95
35	36.5 ± 1.0	17.5	1.00
40	41.5 ± 1.0	20.0	1.00
45	46.5 ± 1.0	22.5	1.00
50	>50	25.0	1.00
60	>60	31.0	1.30
70	>70	36.0	1.30
80	>80	41.0	1.46
90	>90	46.0	1.46
100	>100	51.0	1.46
120	>120	61.0	1.56
150	>150	76.0	1.56
180	>180	91.0	1.56